

# AS20 Series

## Chemical Resistant Anti-Skid Coating



**Product** AS20 Series Chemical Resistant Anti-Skid Coating

**Item Class** Specialty Coating

AS20 is a 2 component, anti-skid polyurethane coating utilized for upper wing marking of escape routes and interior cargo bay flooring. Unlike lacquer-based wing walk coatings, AS20 is resistant to hydraulic fluids and other commonly used solvents. This product is best applied using rolling or brushing techniques.

**Specifications** Product is manufactured to meet the performance requirements of the following specifications:

MIL-W-5044C - SP-J-513-B-0308 - Z-12.512/SP-J-513-B-0308 Ty I

**Catalyst & Additives** Catalyst/Activator

334
331 (Semi-Gloss /Flat)

**Use of Primers** Contact your local 3Chem representative for a complete list of epoxy primers which may be utilized with this system.

**Surface Preparation** Prepare substrate per OEM requirements. Contact your local 3Chem representative for assistance.

**Mixing Instructions**

Base	Catalyst/Activator	Mix Ratio
AS21-XXXX (Gloss)	334	1:1
AS22-XXXX (Semi-Gloss)	331	1:1
AS23-XXXX (Flat)	331	1:1

Shake (Base) for 15 minutes to assure no solid settlement remains in can. Add component B catalyst to component A paint first. Mix ratio for material is 1 part component A paint, 1-part component B catalyst. No thinner should be added to semi-gloss or flat colors. (Kit yield either 2 gallons or 2 quarts). Must ensure mix ratio is exact to obtain desired semi-gloss or flat finish.

**Induction Time** Although no induction time is needed. Once mixed together, ensure that admixed material is continuously stirred for at least 5 minutes before proceeding.

# AS20 Series

## Chemical Resistant Anti-Skid Coating



**Pot Life** 7 Hours @ 21° Celsius, 70° Fahrenheit

**Film Thickness** 3-4 Mils DFT - Wet film thickness should be 5-7 Mils total

### Application Instructions

Temperature and Humidity	Minimum	Maximum
Temperature Celsius	11°	35°
Temperature Fahrenheit	52°	95°
Humidity	33%	74%

Temperature	Dry to Tape	Dry to Handle	Full Cure
52-65°F (11-18°C)	5-6 Hours	7-8 Hours	6 Days
66-85°F (19-29°C)	5-6 Hours	6-7 Hours	6 Days
86-95°F (30-35°C)	5-6 Hours	5-6 Hours	6 Days

Only mix enough material to be applied on initial coat. Always add component B activator to component A paint. Complete kit of material will yield 2 US Gallons (7.5 liters). 1-gallon component A paint, 1-gallon component B activator.

Using a solvent resistant brush or roller, apply one even wet coat of material. A second coat may be applied to increase film thickness or grit amount.

**Application Instructions** PS40 Accelerator (Fast dry additive mix options)

PS40 Accelerator	Dry Between Coats	Dry to Handle	Dry Hard	Pot Life	Full Cure
2% By Volume	12 Minutes	2 Hours	4 Hours	4 Hours	6 Days
3% By Volume	10 Minutes	1 Hours	2.5 Hours	3 Hours	6 Days
5% By Volume	5 Minutes	30 Minutes	1 Hour	45 Minutes	6 Days

\*Note: Overuse of PS40 additive may affect product gloss and finish

**Force Cure:** If deemed necessary oven curing is possible to reduce dry to tape and handle times. After application, allow coating to air dry for 1 hour at room temperature (75° F), then force cure for 2 hours at 120° F.

**Theoretical Coverage** 350-375 sq. ft / gallon @ 1 mil 8-9m<sup>2</sup> / liter @1 mil  
\*Coverage calculated using brushing/rolling techniques

# AS20 Series

## Chemical Resistant Anti-Skid Coating



<b>Color</b>	Available in all color ranges
<b>Gloss</b>	Gloss colors: 90 minimum @ 60 degrees Semi-Gloss colors: 17-30 @ 60 degrees Flat/Matt Colors: Less than 5 @ 60 degrees
<b>Volatile Organic Compound</b>	340 – 390 g/l
<b>Shelf Life</b>	24 Months (When stored in climate-controlled environment between 60-80° F) *Product may be re-certified upon inspection by 3Chem.
<b>Safety Instructions</b>	Always read material safety data sheet (SDS) and product label before utilizing this product. Product SDS is available upon request.

### 3Chem Corporation Disclaimer

All information, recommendations, statements, and technical data contained herein are not intended to be comprehensive or exhaustive, but instead are based on tests utilizing present knowledge and current laws. The accuracy and completeness of said tests are in no way guaranteed, nor should they be construed as an express or implied warranty. We believe such information, recommendations, statements, and technical data to be reliable and accurate, but we have no control over the quality or the condition of the many factors affecting the use and application of the product. The user shall depend upon its/his/her own information, data and testing to determine whether the product is suitable for the user's intended use and the user assumes all risks and liability resulting from its/his/her use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. All products supplied, and technical advice given is subject to our standard terms and conditions of sale. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

\*Brand names mentioned above are either trademarks of or licensed to 3Chem Corporation.